



AMADEUS PRIMO SILK

Technical & Print Specifications

GSM	Caliper um	Bulk cm ³ /g	Brightness %	Opacity %	Roughness ml/min
90	78	0.86	97	92.5	450
100	86	0.86	97	94.5	450
115	92	0.79	97	95	500
130	105	0.8	97	96	450
150	118	0.79	97	96.5	400
170	134	0.79	97	97	350
200	165	0.83	97	97.5	250
250	215	0.86	97	98	200
300	275	0.9	97	98	400
350	325	0.93	97	99	400
380	414	1.09	97	99	400

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen
- HSWO

Finishing

- Varnishing
- Film Lamination
- Foil Blocking
- Embossing
- Folding
- Die Cutting