



PRELUDE HI-BRITE

Technical & Print Specifications

| GLOSS GSM | Caliper um | Bulk cm3/g | Brightness % | Gloss % | Opacity % |
|--------------|---------------|---------------|-----------------|------------|--------------|
| 65 | 52 | 0.8 | 91 | 63 | 91 |
| 70 | 56 | 0.8 | 91 | 63 | 92 |
| 75 | 60 | 0.8 | 91.5 | 63 | 93 |
| 80 | 64 | 0.8 | 92 | 63 | 94 |

| SILK GSM | Caliper um | Bulk cm3/g | Brightness % | Gloss % | Opacity % |
|-------------|---------------|---------------|-----------------|------------|--------------|
| 65 | 59 | 0.9 | 92 | 32 | 92 |
| 70 | 63 | 0.9 | 92 | 32 | 93 |
| 80 | 72 | 0.9 | 93 | 32 | 95 |
| 90 | 81 | 0.9 | 93 | 32 | 96 |

Measurement Criteria

- Caliper - ISO534 um
- Bulk - ISO534 cm3/g
- Gloss Gardner - ISO8254-1 %
- Brightness - ISO2470 (D65) %
- Opacity - ISO2471 %

Finishing

- Varnishing
- Film Lamination
- Foil Blocking
- Embossing
- Folding
- Die Cutting

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen
- HSWO